

**URKI-FAST**

2 K POLYESTER PUTTY

Edition: 022 2014/04

Cod: 5204007035.00000.022

### APPLICATION

URKI-FAST Polyester Putty for the filling of dents, cracks and to repair other irregularities on surfaces in Car Refinish and Commercial vehicle.

Outstands for its adhesion, filling power and flexibility. Adhesion on Galvanized and Zinc Plate Steel.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,85 ± 0,05
Grinding Fineness (μ)	Without lumps
Supply viscosity at 20°C	Thixotropic
%Solids content (weigh / volume)	85 % ± 2 weight; (Mixture with hardener)
V.O.C. (g/l)	< 250 (Ready to use) - (2004/42/CE) IIB (B) (250)
Type of product	Polyester
Colour	Grey 7035

### SURFACE PREPARATION

The surface must be deoxidized and degreased; On Steel previous sanding is recommended. On Zinc plate Steel StarBrite.

Do not use the putty on Wash-Primer or Chromophosphatant Shop-Primer.

Recoatable with any topcoat, once isolated with 2 k Acrylic Filler BESA-CAR or BESA-EXPRESS.

### APPLICATION INSTRUCTIONS

Application: Spatula

Note: Do not add too much hardener in order to avoid bleedings.

The mixture with the hardener can be done on the spatula. Make sure the mixture is correctly done before applying.



E-39  
2-3 % weight



Pot life 3-5'



1000-3000 my



30'



5'



P-80  
P-180

### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	
Gloss 60°-60°	Matt
Second layer	1 - 2 h.

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **12 months** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.