

### URKI-LIGHT

2 K. LOW DENSITY MULTIFUNCTION PUTTY

Edition: 022 2014/04

Cod: 5220001455.00000.022

### APPLICATION

URKI-LIGHT is a HIGH QUALITY Polyester Putty for the filling of cracks and dents in Body Shops. URKI-LIGHT is formulated with special charges improving the conventional putties features:

- It is a "very light" putty which allows an easy application, fineness and total absence of pores.
- Extremely easy sanding, even after 2 days.
- High yield.
- Great Filling power.

MULTIFUNCTION Putty with adhesion on steel, aluminium, Zinc plate steel, galvanized and polyester reinforced with Glass Fibre.

### PHYSICAL PROPERTIES

Density at 20°C (g/cc)	1,30 ± 0,05
Grinding Fineness (μ)	Without lumps
Supply viscosity at 20°C	Tixotropic
%Solids content (weight / volume)	88% ± 2 weight
V.O.C. (g/l)	< 250 (Ready to use) - (2004/42/CE) IIB (B) (250)
Type of product	Polyester
Colour	Beige 1455

### SURFACE PREPARATION

The surface must be deoxidized and degreased; On Steel and GRP previous sanding is recommended. On aluminium sanded and on Zinc plate Steel StarBrite.

Do not use the putty on Wash-Primer or Chromophosphatant Shop-Primer.

Recoatable with any topcoat, once isolated with 2 k Acrylic Filler BESA-CAR or BESA-EXPRESS.

### APPLICATION INSTRUCTIONS

Application: Spatula.

Remark: Do not add too much hardener in order to avoid bleedings.

The mixture with the hardener can be done on the spatula, being sure that the mixture is well homogeneous before application.



E-39  
2-3% weight



Pot life 4-5'



1000-3000 my



30'



5'



P-120  
P-220

### FEATURES OF DRY FILM

Theoretical yield (m <sup>2</sup> /l)	
Gloss 60°-60°	Matt
Second layer	1 - 2 h.

### STORAGE

Keep under cover in a cool and well-ventilated place avoiding direct sunlight. Temperatures between 5 and 30°C recommended.

Can life: **12 months** from manufacturing in date its original unopened container. Consult our Technical Department once date has expired.