



TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY
 TAL.+ 39 - 081 - 876.21.48 r.a. - FAX + 39 - 081 - 876.23.47
<http://www.dichemitaly.com> E-mail: dichem@dichemitaly.com

CODE: 36.328

ACRILUX 2K/HS PLUS "ANTI-SCRATCH"

DESCRIPTION

2K high solid clear acrylic topcoat "Anti-Scratch"
 High gloss retention, excellent flow properties, perfect surface hardness and exceptional good finishing results.
 The well applied film coat will show perfectly spread like it is "mirror coated" without using polish and abrasive paste.

PURPOSE

All types of refinishing after touching-up or complete respray on normal or metallic automotive colours.

COLOURS

Transparent

COVERAGE THEORETICAL

9,5 sqm/mixed litre (dft 50 um)

V.O.C. (g/Lt.) 2004/42/CE

2004/42/IIB(e)(840)510

HARDENER

UNIHard 600

THINNER

DIACRIL

**MIXING RATIO BY VOLUME
2 : 1**

Acrilux 2K/HS PLUS	volume 100 cc	weight 100 gr
Unihard 600	50 cc	50 gr
Diacril	0-5%	0-5%

POT-LIFE

From 1 hour to 3 hours according to hardener version (normal or fast) and temperature

