



# TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY  
TAL.+ 39 - 081 - 876.21.48 r.a. - FAX + 39 - 081 - 876.23.47  
<http://www.dichemitaly.com> E-mail: [dichem@dichemitaly.com](mailto:dichem@dichemitaly.com)

## ACRILUX SUPERFLASH

### DESCRIPTION

2K high solid clear acrylic topcoat VOC 420 g/Lt compliant to European Dir. 2004/42/CE  
High gloss retention, excellent flow properties, perfect surface hardness and exceptional good finishing results.

### PURPOSE

All types of refinishing after touching-up or complete respray on normal or metallic automotive colours.

### COLOURS

Transparent

### BASIC DATA (At 25 deg. C - 50 % R. H.)

#### COVERAGE THEORETICAL

7,7 sqm/mixed litre (dft 50 um)

#### V.O.C. (g/Lt.) 2004/42/CE

420

#### HARDENER

UNIHard 600

#### THINNER

Not necessary

#### MIXING RATIO BY VOLUME 2 : 1

ACRILUX 2K/UHS SUPERFLASH	volume 100 cc	weight 100 gr
UNIHard 600	50 cc	50 gr

#### POT-LIFE

From 1 hour to 3 hours according to hardener version (slow, normal or fast) and temperature

