



# TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY  
TAL.+ 39 - 081 - 876.21.48 r.a. - FAX + 39 - 081 - 876.23.47  
<http://www.dichem.it> - E-mail: [dichem@dichem.it](mailto:dichem@dichem.it)

## TECHNICAL DATASHEET

**PRODUCT: BLACK MATT**

**CODE: DS910**

**PROPERTIES AND AREAS OF USE:** Acrylic paint designed especially to satisfy the needs of professional users. It possesses excellent adhesion characteristics and is suitable for painting metallic materials (iron, brass, aluminium), plastic material, machine tools, doors, windows and shutters. Fast drying and the fact that it can be painted over make it the ideal tool for hobbies and crafts as well as industry.

Features: excellent coverage, non-yellowing, durable, colourfast and lead-free pigments, fast drying, CFC-free.

The 400 ml can covers an area of 1.5 - 2 m<sup>2</sup>, depending on the colour of the paint.

### **SUPPLY SPECIFICATIONS:**

**15 bar foil-coated can**

**Net content**

**400 ml**

**Appearance**

**Can containing pressurized liquid**

**Colour**

**Miscellaneous**

**Scent**

**Typical solvent**

**Density at 20°C**

**0.75 - 0.80 g/ml**

**Pressure at 20°C**

**4.0 ± 0.5 bar**

**Pressure at 50°C**

**8.0 ± 0.5 bar**

**Flammability point**

**less than 0° C**

**Viscosity Ford Cup 4**

**From 11" to 12,5"**

**Remaining dry cylinder**

**From 12% to 23,8%**

**Grit to grindometro**

**From 0 to 2 Micron**

**Gloss**

**From 7 to 92 Gloss**

**Thickness 1 hand**

**11 Micron**

**Thickness 3 hands**

**32 Micron**

**Temperature resistance**

**100 - 120°C**

**Drying time:**

**Dust resistant**

**10 minutes**

**Dry to touch**

**20 minutes**

**Fully dry**

**24 hours**

**May be painted over at any time**

**Childproof patented safety cap**

**Colour reference patch**

### **LABELLING:**



**Directive 2004/42/CE: C.O.V.**

Subcategory: Special finishes

COV value limit: 840 g/Litre

Max. actual contents: 640 g/Litre

Despite being considered reliable, this information is merely issued as a guideline. Its use implicates no liability by our company, including the breach of any patents or licenses. The user is responsible for checking that the product is suitable for the specific use.