



TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY
 TAL.+ 39 - 081 - 876.21.48 r.a. - FAX + 39 - 081 - 876.23.47
<http://www.dichem.it> E-mail: dichem@dichem.it

POLYSTUK 2K EASY GOLD PLUS

CODE: 35.110

DESCRIPTION	<p>Universal polyester filler by spatula application, medium pot-life formulated for the repairing of large surfaces. Excellent sanding, easy to spread and high filling properties.</p> <p style="text-align: center;"><u>Suitable for galvanized plate</u></p>																				
PURPOSE	<p>To use as filler for the repairing of sheet in car and industrial body-work as for industrial coatings (steel, wood, hard plastic, fibertix etc...).</p>																				
COLOURS	<p>Light Yellow Others colours upon request (subject to minimum quantity)</p>																				
HARDENER MIXING RATIO: 3-2-1% According to the temperature POT-LIFE	<p style="text-align: center;">BASIC DATA (At 20 deg. C - 50 % R. H.)</p> <table border="0" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 40%;"></th> <th style="width: 20%; text-align: center; color: red;">< 5-10°C</th> <th style="width: 20%; text-align: center; color: red;">10-20°C</th> <th style="width: 20%; text-align: center; color: red;">20-30°C</th> </tr> </thead> <tbody> <tr> <td>PEROXIDE OF BENZOYLE 50%</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Polystuk:</td> <td style="text-align: center;">100</td> <td style="text-align: center;">100</td> <td style="text-align: center;">100</td> </tr> <tr> <td>Peroxide of benzoyle 50%</td> <td style="text-align: center;">3</td> <td style="text-align: center;">2</td> <td style="text-align: center;">1</td> </tr> <tr> <td></td> <td style="text-align: center;">12-8 min.</td> <td style="text-align: center;">8-5 min.</td> <td style="text-align: center;">5-3 min.</td> </tr> </tbody> </table>		< 5-10°C	10-20°C	20-30°C	PEROXIDE OF BENZOYLE 50%				Polystuk:	100	100	100	Peroxide of benzoyle 50%	3	2	1		12-8 min.	8-5 min.	5-3 min.
	< 5-10°C	10-20°C	20-30°C																		
PEROXIDE OF BENZOYLE 50%																					
Polystuk:	100	100	100																		
Peroxide of benzoyle 50%	3	2	1																		
	12-8 min.	8-5 min.	5-3 min.																		

CODE: 35.110	
APPLICATION METHOD	By spatula
DRYING TIMES BY AIR	30 Minutes
SANDING	After 15 – 30 minutes at 20°C Dry sanding by P80 and refinishing by P120 and P240
STORAGE	12 months (stored in a cool dry place away from direct sunlight).
PACKAGING	Kit 1 Kg gross weight including hardener's tube 20 gr. Kit 2 Kg gross weight including hardeners's tube 40 gr. Kit 5 Kg gross weight including hardener's tube 100 gr.
CARTON	18 x 1 kg Kit - 8 x 2 kg Kit – 4 x 5 kg Kit

Our technical department is at your service for any further details or information you may require.