



TECHNICAL DATA SHEET

VIA MASULLO 1^ TRAV.PRIVATA 80010-QUARTO-(NA)-ITALY
 TAL.+ 39 - 081 - 876.21.48 r.a. - FAX + 39 - 081 - 876.23.47
<http://www.dichem.it> E-mail: dichem@dichem.it

CODE: 35.170

POLYSTUK 2K "Fibreglass"

DESCRIPTION

Fibreglass polyester filler by spatula application, medium pot-life formulated for the repairing of large surfaces. Excellent sanding, easy to spread and high filling properties.

PURPOSE

To use as filler suitable for high thickness applications on car refinishing sheet, most used for repairing, filling and assembling fiberglass vans, used too in nautical industry for all glass wool manufactured articles and generally in bricolage.

COLOURS

Light Yellow
 Others colours upon request (subject to minimum quantity)

HARDENER

PEROXIDE OF BENZOYLE 50%

MIXING RATIO: 3-2-1%
 According to the temperature

< 5-10°C 10-20°C 20-30°C

Polystuk:	100	100	100
Peroxide of benzoyle 50%	3	2	1

POT-LIFE

12-8 min. 8-5 min. 5-3 min.

APPLICATION METHOD

By spatula

DRYING TIMES BY AIR

30 Minutes

SANDING

After 15 – 30 minutes at 20°C
 Dry sanding by P80 and refinishing by P120 and P240

STORAGE

12 months (stored in a cool dry place away from direct sunlight).

PACKAGING

Kit 0,850 Kg gross weight including hardener's tube 20 g
 Kit 1,700 Kg gross weight including hardeners's tube 40 g

CARTON

18 x 0,850 kg Kit - 8 x 1,700 kg Kit

Our technical department is at your service for any further details or information you may require.